### PATENT APPLICATION

# IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re application of

Tomoo MIZUMURA, et al.

PCT Appln. No.: PCT/JP01/01742

Confirmation No.: Not Yet Assigned

Group Art Unit: Not Yet Assigned

Filed: December 14, 2001

Examiner: Not Yet Assigned

For:

IRREGULAR CROSS-SECTIONAL POLYESTER FILAMENTS AND YARN AND

FABRIC CONTAINING SAME

### PRELIMINARY AMENDMENT

Commissioner for Patents Washington, D.C. 20231

Sir:

Prior to examination, please amend the above-identified application as follows:

### IN THE SPECIFICATION:

# Please amend the paragraph bridging pages $1^1$ and 12 as follows:

The above-mentioned requirement (2) defines a ratio of the width of the flat projection part (B) to the width of the triangular part (A), and the ratio is important to cause the resultant irregular cross-sectional polyester filaments and the yarns and fabrics containing the same to obtain a good balance of the creaky touch with the softness and the bulkiness thereof. If the ratio h2/h1 is less than 3.0, the resultant irregular cross-sectional polyester filaments and the yarns and the fabrics containing the same exhibit an unsatisfactory bulkiness. If the ratio is more than 10.0, the melt-spinning procedure for producing the irregular cross-sectional polyester filaments exhibits an insufficient stability and the resultant filaments have uneven quality. The ratio h2/h1 is preferably in the range of from 4.0 to 7.0.

# IN THE CLAIMS:

# Please enter the following amended claims:

- 9. The combined polyester filament yarn as claimed in claim 8, wherein a difference in shrinkage in boiling water between the polyester irregular cross-sectional filaments for the filament component having the lowest shrinkage in boiling water, and the polyester filaments contained in the filament component having a high shrinkage in boiling water and having a highest shrinkage in boiling water, is 4 to 10%.
- 10. The combined polyester filament yarn as claimed in claim 8 or 9, wherein the polyester contained in the polyester filaments having a highest shrinkage in boiling water is a polyethylene trephthalate isophthalate and the content of isophtalic acid in the dicarboxylic acid component of the polyester is 5 to 15 molar%.
- 12. A polyester filament fabric comprising at least one type of yarn selected from the polyester filament yarn as claimed in claim 6 and the combined polyester filament yarn as claimed in any of claims 8 to 11, and having a silk-like hand.

### **IN THE ABSTRACT:**

Please delete the present Abstract of the Disclosure and replace it with the following new Abstract of the Disclosure.

#### **ABSTRACT**

Irregular cross-sectional filaments made from a polyester and yarns and fabrics comprising the filaments, the cross-sectional profile of which filaments has a triangular part (A) and a flat projection part (B) connected to an angular portion of the triangular part and extending therefrom in a flat form, and satisfies the requirements (1) and (2):

$$0.7 \le (L1/L2) \le 3.0$$
 (1)

and

$$3.0 \le (h2/h1) \le 10.0$$
 (2)

in which L1 represents a distance between a middle point of a connection line drawn between two intersecting points of a contour line of the part (A) with a contour line of the part (B), and a projection end point of the part (B); L2 represents a distance between a middle point of the connection line between the part (A) and the part (B), and a middle point of a side line of the part (A) facing the connection line; h1 represents a length of the connection line; and h2 represents a largest width of the part (A) in the direction at right angles to the longitudinal direction of the part (B).

# **REMARKS**

Entry and consideration of this Amendment is respectfully requested.

Respectfully submitted,

SUGHRUE MION, PLLC 2100 Pennsylvania Avenue, N.W. Washington, D.C. 20037-3213 Telephone: (202) 293-7060 Facsimile: (202) 293-7860

SJM/rwl

Date: December 14, 2001

Susan J. Mack Registration No. 30,951

### **APPENDIX**

# VERSION WITH MARKINGS TO SHOW CHANGES MADE

### IN THE SPECIFICATION:

The specification is changed as follows:

The paragraph bridging pages 11 and 12:

The above-mentioned requirement (2) defines a ratio of the width of the flat projection part (B) to the width of the triangular part (A), and the ratio is important to cause the resultant irregular cross-sectional polyester filaments and the yarns and fabrics containing the same to obtain a good balance of the creaky touch with the softness and the bulkiness thereof. If the ratio h2/h1h1/h2 is less than 3.0, the resultant irregular cross-sectional polyester filaments and the yarns and the fabrics containing the same exhibit an unsatisfactory bulkiness. If the ratio is more than 10.0, the melt-spinning procedure for producing the irregular cross-sectional polyester filaments exhibits an insufficient stability and the resultant filaments have uneven quality. The ratio h2/h1h1/h2 is preferably in the range of from 4.0 to 7.0.

### **IN THE CLAIMS:**

## The claims are amended as follows:

- 9. The combined polyester filament yarn as claimed in claim <u>8</u>7, wherein a difference in shrinkage in boiling water between the polyester irregular cross-sectional filaments for the filament component having the lowest shrinkage in boiling water, and the polyester filaments contained in the filament component having a high shrinkage in boiling water and having a highest shrinkage in boiling water, is 4 to 10%.
- 10. The combined polyester filament yarn as claimed in claim 8 or 97 or 8, wherein the polyester contained in the polyester filaments having a highest shrinkage in boiling water is a polyethylene trephthalate isophthalate and the content of isophtalic acid in the dicarboxylic acid component of the polyester is 5 to 15 molar%.

12. A polyester filament fabric comprising at least one type of yarn selected from the polyester filament yarn as claimed in claim 6 and the combined polyester filament yarn as claimed in any of claims 8 to 117 to 11, and having a silk-like hand.